


U-STUCCO™ XPX LIGHT-WEIGHT MULTI-PURPOSE INSULATIVE BASE COAT STUCCO

U-STUCCO™
GREEN BUILDING MATERIALS



FEATURES & PROPERTIES



**ONE COAT
APPLICATION**



**SINGLE DAY
APPLICATION**



**66% LOWER
LABOR COST**



**TROWEL
OR SPRAY-ON**



**ULTRA
LIGHT-WEIGHT**



**HIGH CRACK
RESISTANT**



**SCRATCH, BROWN
& FINISH COAT**



**LESS SCAFFOLD
EXPENSES**



EASY TO APPLY



**UP TO 7 TIMES
MORE COVERAGE**



**WATER
RESISTANT**



**MOLD
RESISTANT**



**CORROSION
RESISTANT**



**VAPOR
PERMEABLE**



FIREPROOF



R 1.6/INCH



**THERMAL
INSULATION**



**CONTINUOUS
INSULATION**



**CALIFORNIA
TITLE 24 COMPLIANT**



**GREEN BUILDING
MATERIAL**



**SUITABLE
FOR PRECAST**



SANDABLE



V.O.C. FREE



**40% RECYCLED
CONTENT**



**LEED
FRIENDLY**



**U.V.
REFLECTIVE**



**IDEAL FOR
RESTORATION**



**DIRECT APPLICATION
ON VARIOUS SUBSTRATES**



**ACOUSTIC
INSULATION**



**LESS FREIGHT
EXPENSES**

/// U-STUCCO™ XPX

LIGHT-WEIGHT MULTI-PURPOSE INSULATIVE BASE COAT STUCCO

IDEAL FOR EPS/XPS/EIFS/ICF APPLICATIONS

PRODUCT COMPOSITION

U-STUCCO™ XPX is a high-quality blend of white portland cement and mineral based lightweight aggregates that conforms to ASTM C926 which is developed as a replacement to job-site mixed scratch & brown base coat stucco. U-STUCCO™ XPX meets code criteria for exterior portland cement plaster.

MATERIAL STANDARDS

Cement : ASTM C150

Light Weight Aggregate : ASTM C330 / C332

PRODUCT HIGHLIGHTS

- Gain up to 1.6 R value per inch without the addition of any rigid foam board.
- Covers “thermal breaks” in wall assemblies and significantly enhance any structure’s insulation performance and energy efficiency.
- Provides superior fire-resistance, water-resistance, moisture protection and thermal insulation compared to conventional stucco.
- Apply in a single pass of up to 1” to nearly any substrate, including plywood, OSB, CMU blocks, concrete, metal, AAC, EPS, XPS, ICF and plastic substrates.

DESCRIPTION

Meet U-STUCCO™, industry’s lightest ‘true’ one-coat stucco that is revolutionizing the stucco industry with its thermal, fire, water and acoustic insulation properties. It’s an ultra light-weight (*1/6th weight of the conventional stucco*) hydrophobic, high crack and corrosion resistant, UV reflective, ready-to-use powder-mix product. It provides fire resistance (*2hr rated @1200°C/ 2192°F*) as well as thermal (*up to R 1.6 per inch*), water and acoustic insulation (*36 dB*).

U-STUCCO’s simple one-coat application process greatly reduces time and labor expenses and renders traditional 3-coat application obsolete. U-STUCCO™ can be applied in a single pass of up to 1 inch to nearly any substrate, including plywood, OSB, gypsum, masonry, AAC, steel, foam and plastic substrates.

U-STUCCO™ is ideal for achieving superior energy efficiency. It can be used in conjunction with EPS, XPS, ICF or Fiberglass (Mineral Wool) to create wall assemblies with higher insulation R values and improved crack and water-resistance complying with California Title 24 code helping you build sustainable and energy efficient living spaces. U-STUCCO™ XPX may also be used over wood or gypsum backing and as a scratch and brown coat application for traditional stucco systems.

U-STUCCO™ is 99% inorganic and contains 40% post-consumer recycled content making it a true green product. It is a Class 1 (A1) non-flammable material therefore it doesn’t burst into flame or emit any toxic gas when exposed to fire. It allows your building to breathe and prevents mold and mildew.

APPLICATION AREAS

U-STUCCO™ XPX can be used both in new construction and renovation projects. It can be applied on various substrates such as OSB, plywood, concrete, cinder blocks, bricks, densglass, drywall, sheetrock, EPS, XPS, ICF, AAC, wood and steel structures.

APPLICATION METHODS

Apply by hand trowel or plaster gun.

APPLICATION TEMPERATURE

Ambient and surface temperature must be between +40°F (+5°C) and +95°F (+35°C). Try avoiding application under extreme wind, cold or direct sunlight conditions or when temperatures may fall outside this range within 24 hours of application. Provide supplemental heat and protection from precipitation as needed.

SURFACE PREPARATION

The application surface must be structurally sound, clean, free of dust, mold, dirt, silicones and paint products which may affect the ability of U-STUCCO™ XPX to bond to the surface. Major cracks, holes or voids should be repaired prior to application. The surface shall be wet especially at highly porous and absorbing surfaces or at high temperatures. On lathed construction, apply to lathing installed in accordance with ASTM C1063. U-STUCCO™ XPX requires water-resistive barrier installed and flashed in accordance with the building code and to form a water-shedding surface. Install Water Resistive barrier (type and method of application) per manufacturer's Guide or Specifications. Do not apply to substrates which are frozen or contain frost or ice.

For application to very dense or smooth concrete and additional surface preparation options, contact U-STUCCO™ USA Technical Support.

MIXING

Pour U-STUCCO™ XPX 44 lb (20 kg) bag into a mixing container, followed by 4.0 to 4.2 gallons (15 to 16 lt) of cool, clean potable water (*let hose run to clear it of hot water*) and mix for approximately 8 minutes. For the mixing process, a hand mixer or plastering machine can be used. Mixing should be done mechanically at a high speed until the mixture reaches a homogenous consistency and workability.

Mix same size batches using the same amount of water, to ensure consistency. Briefly re-mix before using (*approximately 1 minute*). Only U-STUCCO™ USA approved additives can be added to this product.

APPLICATION

Thoroughly dampen concrete and masonry substrate if necessary before applying U-STUCCO™ XPX. Apply by hand trowel or plaster gun to a minimum thickness of approximately 1/4 inch (5 mm) On lathed construction the total thickness can be up to 1 inch (25 mm) Using a trowel or plaster pump, apply U-STUCCO™ XPX to the properly prepared surface. Always float the material uniformly to provide a surface receptive to the application of the finish coat. Sand or smooth finish can be easily achieved after 1 to 3 hours after the application depending on the ambient temperature and application thickness. Various finishes can be achieved with different techniques. Always allow U-STUCCO™ XPX to dry thoroughly before applying acrylic primers or finishes.

Read the entire label before using this product. All materials are to be installed in compliance with local building code requirements, ASTM C926, C1063 and U-STUCCO™ USA's specifications.

APPLICATION THICKNESS

The minimum thickness over any substrate is ¼ inch (5 mm). Some assemblies may require specific minimum thickness. U-STUCCO™ XPX can be applied up to 1 inch (25 mm) thickness with a single pass.

CURING

Curing time may vary due to ambient temperature, surface temperature, surface porosity, application methods, and thickness of material. All freshly applied material must be protected by an approved protective system from inclement weather until fully dry.

WORKING TIME

Sets in 90 to 120 minutes after mixing, depending on temperature, humidity and substrate conditions.

COVERAGE

Approximate Coverage, depending on the condition of substrate and the thickness of application is based on uniform thickness and zero waste factor. **44 lb (20 kg) bag of U-STUCCO™ XPX will cover approximately;**

Imperial	Thickness	Coverage
XPX 44 LB	1/4 inch	84.58 sq ft
	1/2 inch	42.29 sq ft
	3/4 inch	28.19 sq ft
	1 inch	21.14 sq ft

Metric	Thickness	Coverage
XPX 20 KG	5 mm	10.00 sq mt
	10 mm	5.00 sq mt
	15 mm	3.33 sq mt
	20 mm	2.50 sq mt

Coverage may vary due to ambient temperature, surface temperature, surface porosity, mixing methods, application methods, amount of water, wall type and metal lath type. Coverage must be verified in the field using the same procedures and conditions that will be present at the project.

PACKAGING AND STORAGE

Available in 44 lb (20 kg) net weight in a multi-layer moisture resistant bag. Store off ground and protect from rain and moisture. Storage space temperature should be no lower than +40°F (+5°C)

HEALTH AND SAFETY

It may be irritant to eyes and skin when exposed. Wear appropriate dust, skin and eye protection. In case of eye contact, flush immediately with water and consult a physician. Wash hands with soap and water after use. Keep out of reach of children. For more information on handling this product refer to its material safety data sheet (SDS). The most current SDS can be found on www.ustucco.com

QUALITY MANAGEMENT

U-STUCCO™ Green Building Materials are produced under ISO 9001:2008 quality standards. The product quality is monitored according to the EN 998-1 by U-STUCCO™ USA, LLC in the factory laboratories.

LIMITED WARRANTY


U-STUCCO™ XPX is warranted to perform in accordance with the product specification when used pursuant to the application instructions. This warranty is limited to and shall not exceed the total amount paid by the buyer for the product here under. In no event U-STUCCO™ USA, LLC shall be liable for any loss of profits, special or consequential damages in respect to any claim. The foregoing warranties are in lieu of all other warranties express or implied including those concerning suitability for a particular use.

This product data sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about the guidelines for the proper use and application of the covered product(s) under normal environmental and working conditions. Because each project is different, U-STUCCO™ USA, LLC cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

IMPORTANT NOTICE TO USER

This information is designed to guide you and has been conscientiously compiled according to the latest state of our technology. U-STUCCO™ USA assumes no liability, expressed or implied, in connection with the use of the product because of the great variety of applications and working conditions.

NOTES



U-STUCCO™ USA

13488 Maxella Ave #630
Marina Del Rey, CA 90292
United States

Technical Support +1 (424) 542 5353
info@ustucco.com www.ustucco.com



	Conventional Stucco	EIFS	U-STUCCO™
“TRUE” ONE COAT APPLICATION	—	—	+
SINGLE DAY APPLICATION	—	—	+
LOW LABOR COST	—	—	+
FASTER SCAFFOLDING TURNAROUND	—	—	+
LESS FATIGUE ON LABOR FORCE	—	—	+
EASY TO APPLY (DIY)	—	—	+
THERMAL INSULATION (R VALUE)	—	+	+
CONTINUOUS INSULATION	—	—	+
ULTRA-LIGHT WEIGHT	—	+	+
UV REFLECTIVE	—	—	+
A1/ CLASS 1 FIRE RESISTANT	—	—	+
WATER RESISTANT & HYDROPHOBIC	—	—	+
PERMEABLE	+	—	+
MOLD & MILDEW RESISTANT	—	—	+
CORROSION RESISTANT	—	—	+
HIGH CRACK RESISTANT	—	—	+
IDEAL FOR RESTORATION	—	—	+
SUITABLE FOR PRECAST MOULDING	—	—	+
LESS FREIGHT EXPENSES	—	—	+
LOW CARBON FOOT PRINT	—	—	+
RECYCLED CONTENT	—	—	+
V.O.C FREE	+	—	+
SANDABLE	—	—	+
ACOUSTIC INSULATION	—	—	+
LEED & TITLE 24 COMPLIANT	—	+	+
GREEN BUILDING MATERIAL	—	—	+